

TECHNICAL DATA SHEET

Thickness: 6.0 MM

PRODUCT TECHNICAL SHEET CENTONI COMPACT SPLASHBACKS

Compact High Pressure Laminates (HPL) as per EN 438-4:2016

SR.NO.	PROPERTIES	TEST METHOD	UNIT OF MEASUREMENT	ATTRIBUTES OF PERFORMANCE	RESULTS (AS PER EN 438-4)
				EN-438 LAMINATE CLASSIFICATION Type CGS	
1	SURFACE QUALITY				
1.1	Surface Quality	EN 438-2.4	mm ² /m ²	Spots, dirt and similar surface defects	≤ 1
			mm/m ²	Fibers, hairs, and scratches	≤ 10
2	DIMENSIONAL PROPERTIES / STABILITY				
2.1	Thickness	EN 438-2.5	mm	5.0 ≤ t < 8.0mm : ± 0.40 mm	5.0 ≤ t < 8.0mm : ± 0.40 mm
2.2	Size	EN 438-2.6	mm	Length and Width +10/-0	+ 05 / - 0
2.3	Straightness of edges	EN 438-2.7	mm/m	Straightness of edges ≤ 1.5	≤ 1
2.4	Squareness	EN 438-2.8	mm/m	Squareness ≤ 1.5	≤ 1
2.5	Flatness (measured on full size sheet)	EN 438-2.9	mm/m	For 2.0 ≤ t < 6.00mm : 8	5
			mm/m	For 6.0 ≤ t < 10.00mm : 5	3
			mm/m	10.0 ≤ t : 3	2
3	PHYSICAL PROPERTIES				
3.1	Resistance to Surface Wear	EN 438-2.10	Revolutions	Wear Resistance - Initial Point	Unicolours - ≥ 200 Printed Décor - ≥ 175
			Revolutions	Wear Resistance - Wear Value	Unicolours - ≥ 450 Printed Décor - ≥ 410
3.2	Resistance to immersion in Boiling water	EN 438-2.12	%	Mass Increase - 2 ≤ T < 5 mm	≤ 2
			%	Mass Increase - T ≥ 5 mm	≤ 1
			%	Thickness Increase - 2 ≤ T < 5 mm	≤ 2
			%	Thickness Increase - T ≥ 5 mm	≤ 1.5
			Rating	Surface Rating - Gloss Finish	≥ 4
			Rating	Surface Rating - Other Finishes	≥ 5
3.3	Resistance to water vapour	EN 438-2.14	Rating	Edge Rating - Other Finishes	≥ 4
			Rating	Appearance - Gloss Finish	≥ 4
3.4	Resistance to Dry heat @160°C	EN 438-2.16	Rating	Appearance - Other Finishes	≥ 4
			Rating	Appearance - Gloss Finish	≥ 4
3.5	Dimensional stability at elevated temperature	EN-438- 2.17	Longitudinal %	Cumulative dimensional change 2 ≤ T < 5 mm	≤ 0.40
			Transversal %		≤ 0.80
			Longitudinal %	Cumulative dimensional change T ≥ 5 mm	≤ 0.30
			Transversal %		≤ 0.60
3.6	Resistance to impact by large diameter ball	EN-438- 2.21	mm	2 ≤ 6mm - 1400mm	≥ 1500
			mm	T ≥ 6mm - 1800mm	≥ 1900
3.7	Resistance to crazing	EN-438-2.24	Rating	Appearance	≥ 4
3.8	Resistance to Scratching	EN-438-2.25	Rating	Appearance - Smooth Finishes	≥ 3
			Rating	Appearance - Textured Finishes	≥ 3
3.9	Resistance to Staining	EN-438- 2.26	Rating	Appearance - Group 1 & 2	5
			Rating	Appearance - Group 3	5
3.10	Light Fastness (Xenon Arc)	EN-438-2.27	Degree	Contrast	5
3.11	Flexural Modulus	EN-ISO-178-2003	Mpa	Stress ≥ 9000	9000-11500
3.12	Flexural Strength	EN-ISO-178-2003	Mpa	Stress ≥ 80	≥ 120
3.13	Tensile Strength	EN-ISO-572-2-1996	Mpa	Stress ≥ 60	60-90
3.14	Density	EN-ISO 1183-1:2004	gm/ cm ³	≥ 1.35	≥ 1.4
4	FIRE PERFORMANCES				
4.1	Fire Reaction Classification - CGS	EN 13501-1	Test as per EN 13823 and EN ISO 11925-2 (Small-burner test)		
			Rating	Classification for T ≥ 12 mm	C – s1, d0
			Rating	Classification for 6 ≤ T < 12 mm	D – s2, d0
5	OTHER PROPERTIES				
5.1	Release of Formaldehyde	EN-438-7.4.11.1	Rating	Classification	E1

Remarks

@ Required Values Based on EN-438 - 4 ISSUE-02:-Date:-12.03.2022